

Synthesis and Characterization of Nano Hydroxyapatite with Polymer Matrix Nano Composite for Biomedical Applications

P.Sakthivel^{1*}, and A.Ragu¹

Abstract—Hydroxyapatite is chemically similar to the mineral component of bone and teeth. A novel nano composite involving nHAp/polymer matrix has been successfully synthesized by wet chemical precipitation method at room temperature. The purpose of synthesizing such nano composite is due to its wide range of properties like biocompatibility, bioactivity, cytotoxicity and mechanical properties. The FTIR spectra of nHAp/polymer matrix indicated significant intermolecular interaction between the various vibrational modes corresponds to phosphate and hydroxyl groups. The results of XRD, TGA/DTA suggested its crystallinity and thermal stability. The size and morphology of the sample were characterized using Transmission Electron Microscopy (TEM).

Keywords— FTIR, TGA/DTA, TEM, XRD.

I. INTRODUCTION

HYDROXYAPATITE (HAp) which has molecular stoichiometric formula $\text{Ca}_{10}(\text{PO}_4)_6(\text{OH})_2$, has been extensively investigated due to its excellent biocompatibility, bioactivity and osteoconductivity as well as its similarities to the main mineral component of bone. However, it has been reported that HAp in the form of powders, used for the treatment of bone defect, has problems associated with migration to places other than implanted areas. Among them, hydroxyapatite is frequently used in orthopedic, dental and maxillofacial applications, meaning that it supports bone growth and osteointegration [1-3]. Recently, research on the functional bone substitutes such as apatite has been a major subject over the year [4]. Belonging to the family of apatite, nHAp has been widely used as artificial bone substitutes in biomedical applications because of its excellent bioaffinity, osteoinductivity and nanoproperties [5]. Several methods are available for synthesizing HAp based nano structured materials like co-precipitation, sol-gel, and reverse microemulsion, hydrothermal and solid state reaction [6]. Co-precipitation from a apatite polymer matrix aqueous solution is one of the effective and economic methods for nHAp preparation [7]. The microstructure and property of the resulting nHAp powder greatly depends on the properties of the polymer matrix. Hence, in recent years considerable

attention has been focused towards the development of polymer composites to fulfill the requirement for biomedical applications.

Some excellent reviews have discussed the various types of degradable polymers and their co-polymers [8-14]. Therefore, this subject will not be discussed in detail in this review. The scope of this paper is to give a perspective of the facts that enter into bone tissue engineering using degradable polymers in particular. Recently, the characteristic of a degradable polymer prior to implantation have been divided into two main categories: biocompatibility and biofunctionality [15]. Biocompatibility refers to the aspects concerning the absence of toxicity, immunogenicity, carcinogenicity and thrombogenicity [15]. Biofunctionality refers to the aspects of adequate properties (mechanical, physical, chemical, thermal and biological) easy to handle, sterilizable, storable and resorbable [15]. Various types of polymers have been combined with calcium phosphates (mainly hydroxyapatite) to prepare nano composites with improved biocompatible and mechanical properties [16-18]. Synthetic polymers were studied as potential matrices of composite materials with hydroxyapatite (HAp) for possible application as bone analogues: Polymethyl methacrylate and Poly vinyl pyrrolidone. Several studies have investigated the synthesis and characterization of hybrid materials based on HAp and biodegradable POLYMERS.

II. MATERIALS AND METHODS

Materials

The raw materials required to start the processing of the composite were: analytical grade Calcium hydroxide ($\text{Ca}(\text{OH})_2$) was purchased from Sigma Aldrich and ammonium dihydrogen phosphate ($(\text{NH}_4)_2\text{H}_2\text{PO}_4$) procured from Mercy (Mumbai, India). Poly vinyl pyrrolidone (mol.wt 40000) was purchased from Sigma Aldrich and Poly methyl methacrylate were purchased from Alfa Aesar. Doubly distilled water with ethanol was used as the solvent.

Methods

III. SYNTHESIS OF HAP/PMMA AND PVP NANO COMPOSITES

The First calcium hydroxide was slowly added to a solution

^{*}, 1, Department of Physics, Urumu Dhanalakshmi College, Kattur, Tiruchirappalli, India.620019. email id: physicsragu@gmail.com, sakthiphy13@gmail.com.

of ammonium dihydrogen phosphate and after proper mixing, the HAp was precipitated by adding ammonia and PH of the solution was maintained from 9 to 11. The solution was constantly stirred for 24h by magnetic stirrer, allowing the reaction to complete. The resultant precipitate was separated and ammonia was removed by repeated washing. The precipitate was allowed to dry in an oven at 90°C subsequently; aggregates formed were crushed into fine powder. In a separate study synthesized HAp powder (80) was mixed with polymer solution (20) where number denotes the wt% and the resultant HAp - PMMA and PVP composite powder was thoroughly mixed using a mortar and pestle for 30 min.

IV. RESULT AND DISCUSSION

FTIR

The Prepared samples were studied by Fourier Transform Infrared Spectroscopy (FTIR) using Perkin Elmer spectrometer in the range of 400 cm^{-1} to 4000 cm^{-1} . The FTIR spectra of pure nHAp with PMMA and PVP composites are shown in figure1. The peak observed at 3142.93 cm^{-1} corresponds to the stretching mode of -OH group, which characterizes the presence of calcium phosphate such as HAp. The characteristic band of PMMA, absorption of C=O, -CH₂- appeared at 2791.56, 2364.02, 1462.74 and 875.62 cm^{-1} respectively. The bands located at 1034.18 cm^{-1} is attributed to the PO₄³⁻. It is confirmed with the report presented (Urch et al 2009) at 1292.13 cm^{-1} and 1662.85 cm^{-1} confirms the presence of polymer (PVP). The observed bands at 602.59 cm^{-1} are due to phosphate stretching mode is appeared at 565.02 cm^{-1} corresponds to PO₄³⁻ group.




Fig.1. FTIR Spectrum of nHAp With Polymer Matrix.

XRD

X-ray diffraction pattern, typical of the composites, is shown in fig (2). The strong peaks present in the XRD patterns were readily indexed with the nano composites shows the most intense peaks 211 and 212 at $2\theta=31.5^\circ$, 38.5° attributed to HAp. Then polymer matrix peaks are observed at 202, 213. The broad peaks and very wide baseline

in the powder pattern indicate that the structure has the inorganic component. The patterns were in good agreement with JCPDS (09-0432) and confirmed to the pure phase of HAp and polymer matrix. If it is calculated from the spacing of peaks that the particle size of HAp crystalline size is varied from length (20 nm to 100 nm) and width (2 nm to 4 nm).




Fig.2. XRD Of nano HAp/ Polymer Matrix

TEM

The structure and morphology of the samples were further confirmed by the TEM images of the prepared hydroxyapatite with polymer matrix as shown in fig. (3). The micrographs reveal that synthesized HAp with polymer contains rod-like morphology of length varying from 20 to 100 nm and width varying from 2 to 4 nm. The particle size is also found to be in agreement with the report results of (Ferraz et al. 2004). From TEM images, the HAp is visible as dark contrast areas and seen uniformly dispersed throughout the polymer matrices. In addition, the selected area electron diffraction (SAED) of the precipitates shows that diffraction ring of patterns. It implies that the precipitates are crystalline in nature. This is in agreement with XRD results.




Fig.3 (A), (B), (C) TEM Images And (D) Selected Area Electron Diffraction (SAED) Image Of nano HAp/Polymer Matrix.

TGA/DTA

The TGA (fig.4) of the HAp/Polymer matrix nanocomposite powder was carried out between 30 to 800 °C in air at a heating rate of 25 °C/min. The decomposition behavior of hydroxyapatite/ polymer matrix nanocomposite is shown in fig.4. The nanocomposite content is calculated from the residual weight in TGA curves at 550°C. However, it is very difficult to control adsorbed water content in the composites. In the TGA curves several steps are observed (Rajendran et al. 2002; Singh et al. 2008; Wang et al. 2007). The first step, showing a small decrease in weight, is associated with the removal of adsorbed water, when heated above 90°C. The second step from 220 to 360°C may be due to the dehydration reaction of C-OH groups in PVP chains. The DTA curve shows that there is an indication of endothermic sharp peaks at 360°C. Similarly the other endothermic peaks in the curve at 540°C. However, at 60°C a sharp exotherm is observed which indicates the crystallation of Hap.




Fig.4. Thermal Analysis Of Nano HAp/Polymer Matrix.

V. CONCLUSION

Calcium phosphate (Hydroxyapatite) materials have been used extensively for bone replacement and augmentation due to their similarity to the mineral component of bone. The formation of hydroxyapatite nano particles was confirmed by X-ray diffraction (XRD) and Fourier Transform Infrared Spectroscopy (FTIR). The rod-like shaped particles were confirmed through the Transmission Electron Microscopy (TEM). The particle size around 20 to 100 nm and width varying from 2 to 4 nm have been observed. The thermal analysis of TGA-DTA was carried out to investigate the thermal stability of the powder. The nHAp with nano polymer matrix produced can be highly useful as a bone replacement material.

ACKNOWLEDGMENT

Authors thanks to the management of Urumu Dhanalakshmi College, Tiruchirappalli for providing research facilities in the campus.

REFERENCES

- [1] C.J. Damien, J.R. Parsons: Bone graft and bone graft substitutes. A review of current technology and applications, *Journal of Applied Biomaterials*, 2, 187-208 (1991).
- [2] H.Aoki; Science and medical applications of hydroxyapatite. Ishiyaku Euro America, St. Louis (1994)
- [3] R.Murugan, S.Ramakrishna; Nano structured biomaterials, in 'Encyclopedia of Nanoscience and Nano technology' (ed.: H.S.Nalwa) American scientific publishers, Stevenson Ranch, Vol 7, 596-613 (2004).
- [4] H. Zhou, J.Lee. Nanoscale hydroxyapatite particles for bone tissue engineering. *Acta Biomaterials*, 2011, 7(7): 2769-2781.
- [5] K.Thanigaiarul, K.Elayaraja, P.Magudapathy, U.Kamachi Mudali, K G M Nair, M.Sudarsan, J B M. Krishna, A.Chakraborty, S. Narayana Kalkura surface modification of nanocrystalline calcium phosphate bioceramic by low energy nitrogen ion implantation. *Ceramics International*, 2013, 39(3): 3027-3034.
- [6] Ferraz MP, Monteiro FJ, Manuel CM. Hydroxyapatite nanoparticle: A review of preparation methodologies. *Journal of applied Biomaterials & Biomechanics*; 2004; 2: 74-80
- [7] X Y Pang, X. Bao. Influence of temperature, ripening time and calcination on the morphology and crystallinity of hydroxyapatite nanoparticle, *Journal of the European Ceramic Society*, 2003,23(10): 1697-1704.
- [8] P.I.Wuismani, T.H.Smit, *Biodegradable polymers materials* 2009, 2, 307-344.
- [9] L.S.Nair; C.T.Laurencin., *Polymers as biomaterials for tissue engineering and controlled drug delivery*. *Adv. Biochem. Eng. Biotechnol.* 2006, 102, 47-90.
- [10] T.A. Holland; A.G.Mikos, *Biodegradable polymeric scaffolds. Improvements in bone tissue engineering through controlled drug delivery*. *Adv. Biochem. Eng. Biotechnol.* 2006, 102, 161- 185.
- [11] K. Rezwani, Q. Z. Chen; J.J.Blaker, A.R.Bouaccini. *Biodegradable and bioactive porous polymer/ inorganic composites scaffolds for bone tissue engineering*. *Biomaterials* 2006, 27, 3413-3431.
- [12] M.Vert, poly (lactic acids). In *Encyclopedia of Biomaterials and Biomedical engineering*; marcel Dekker Inc.: New York, NY, USA, 2004; PP.1254-1263.
- [13] P.A.Gunatillake; R.Adhikari. Recent developments in biodegradable synthetic polymers. *Biotechnol. Annu.Rev.*2006,12, 301-347.
- [14] P.A.Gunatillake; R.Adhikari, *Biodegradable synthetic polymers for tissue engineering*. *Eur.cell mater.*2003, 5, 1-16.
- [15] M.Vert, *Degradable and bioresorbable polymers in surgery and in pharmacology: Beliefs and fact*. *J.Mater.sci.mater.med.*2009, 20, 437 - 446.
- [16] Mourino V, Boccaccini AR. Bone tissue engineering therapeutics: controlled drug delivery in three- dimensional scaffolds. *J R Soc Interface*. 2010;7:209-27. doi:10.1098/rsif.2009.0379.
- [17] Porter JR, Ruckh TT, Popat KC. Bone tissue engineering: a review in bone biomimetics and drug delivery strategies. *Biotechnol Prog.* 2009; 25:1539-60. doi:10.1002/btpr.246.
- [18] Neuendorf RE, Saiz E, Tomsia AP, Ritchie RO. Adhesion between biodegradable polymers and hydroxyapatite: relevance to synthetic bone-like materials and tissue engineering scaffolds. *Acta Biomater.* 2008; 4:1288-96. doi:10.1016/j.actbio.2008.04.006.